

TECHNICAL DATA- GU-30

HIGH PERFORMANCE POLYURETHANE

DESCRIPTION:

GU-30 is a three-component, non-yellowing, high solids, aliphatic polyurethane floor sealer for concrete & cement-based overlays. GU-30 high solids polyurethane is ideal as a top finish coat on epoxy systems and concrete that exhibits excellent characteristics for abrasion resistance, chemical resistance, flexibility, weathering, and UV stability. GU-30 high solids polyurethane is recommended for concrete coating, laboratories, gyms, residential interiors, auto service centers, bars, clubs, retail stores cafeterias, and chemical exposure areas and more.

SPECIFICATIONS:

RECOMMENDED FILM THICKNESS:

3-5 mils per coat wet thickness (Do not apply thicker)

COVERAGE PER GALLON:

360 to 600 square feet (33.5m² to 56m²) @ 3-5 mils wet thickness

PACKAGING INFORMATION

1 gallon and 4-gallon kits

*1-gallon kit = 1-pint part A, 0.7 gal. part B, 3 lb. part C (volumes approximate)

*4-gallon kit = 0.5 gal. part A, 2.74-gal part B, 12 lb. part C (volumes approximate)

MIX RATIO:

1.08 lb. part A with 6.45 lb part B and 3.0 lb part C (weights approximate)

SHELF LIFE:

1/2 year in unopened containers

SOLIDS BY WEIGHT:

Mixed= 93%

SOLIDS BY VOLUME:

Mixed= 92%

VOLATILE ORGANIC CONTENT:

Less than 95 grams per liter

PRODUCT STANDARD COLORS:

Opaque clear.

FINISH CHARACTERISTICS:

Semi-Gloss / Eggshell (20-40 at 60 degrees @ glossmeter)

ABRASION RESISTANCE:

Taber abrasor CS-17 calibrase wheel with 1000-gram total load and 500 cycles= 15-20 mg loss

ADHESION:

>300 psi @ elcometer (concrete failure, no delamination) over suitable primer

VISCOSITY:

Mixed = 1000-2000 cps (normal)

IMPACT RESISTANCE: Gardner Impact, direct & reverse=160 in lb. (passed)

DOT CLASSIFICATIONS:

- *Part A-“NA1993, COMBUSTIBLE LIQUID N.O.S., 3, PG III”
- *Part B-“ENVIRONMENTALLY HAZARDOUS SUBSTANCES, LIQUID, N.O.S., UN3082, 9, PGIII,”
- *Part C- “Not Regulated”

CURE RATES: 70F (21C) at 1 gal volume

pot life – 150-gram mass..... 1-2 Hours
tack free (dry to touch)3-6 hours
recoat or topcoat..... 6-10 hours
light foot traffic.....14-24 hours
full cure (heavy traffic) ... 3-5 days

APPLICATION TEMPERATURE:

50-90 degrees F (10-32C) with relative humidity between 50% and 90%.

CHEMICAL RESISTANCE:

REAGENT	RATING
Gasoline	D
MEK	B
20% Nitric Acid	C
Ethylene Glycol	D
50% sodium hydroxide	D
10% sulfuric acid	D
5% acetic acid	C

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion.
NOTE: extensive chemical resistance information is available through your sales representative.

PRIMER:

Recommended GE-10W clear, GE-C10W pigmented

TOPCOAT:

None recommended

LIMITATIONS:

* Color or gloss may be affected by chemical exposure, temperatures application & humidity, exposure to lighting such as sodium vapor lights & thickness. For the best result use a high quality 3/8" nap roller. Slab on grade requires moisture barrier Substrate temperature must be 5°F above dew point All new concrete must be cured for at least 30 days Physical properties are typical values and not specifications Tire contact may cause staining and discoloration Colors may vary from batch to batch, therefore, use only product from the same batches for an entire job. See reverse side for application instructions. See reverse side for limitations of our liability and warranty. Do not use if relative humidity is below 25% Material has to be applied at the recommended thickness per gallon uniformly for proper appearance and development of physical properties. The epoxy basecoat must be abraded/de-glossed for proper adhesion.

MIXING AND APPLICATION INSTRUCTIONS (GU-30)

- 1) **PRODUCT STORAGE:** Store GU-30 polyurethane between 60 and 90 degrees F(16-32 C). Have material at room temperature before using. Do not freeze. Do not keep next to a heat source or direct sunlight. Keep away from flames, sparks and any other combustion hazards.
- 2) **SURFACE PREPARATION** Prepare surface according to the type of complete system to be applied. All dirt, oil, dust, sealers, paint and other contaminants should be removed to assure proper bonding to the substrate. Use mechanical scarification or acid etching until a desirable result is achieved. Diamond grinding or shot blasting is recommended for the best result. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.
- 3) **MIXING AND HANDLING** GU-30 polyurethane has a three-component ratio by weight-merely mix 1.08 lb. of part A, 6.45 lb. of part B, and 3 lb. of part C. After the three parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Avoid whipping air into the coating. Improper mixing may result in product failure. Catalyzed product should be placed on the floor within 30 minutes. If left in the pail too long, product will cure at an accelerated rate rendering it useless.
- 4) **PRODUCT APPLICATION:** Mixed polyurethane can be applied by brush or roller. Maintain temperatures within the recommended ranges during the application and curing process. Properly prime the substrate. It is best to maintain a wet edge to avoid roller marks. Direct sunlight or high temperatures may cause visible roller marking during application. Uneven application thicknesses may cause variations in gloss, therefore apply material as evenly in thickness as possible. Too thick of an application may result in solvent entrapment and product failure. Although the pot life may appear to be longer, do not apply after two hours after the three components have been mixed at 1 lb. Once mixed, air exposure might cause a slight skinning on the surface in the roller pan or container if left uncovered, even for a few minutes. If skinning occurs, remove the thin layer, then stir and continue to use the product for up to two after it has been mixed. Material left unused in the mixing pail or application tray may expand and foam up after an extended period of time. Avoid application on extremely cold or hot days or during wet, foggy weather. Basic rules include: Apply with ambient and surface temperatures ranging above 50°F (10°C) and below 90°F (32°C) and that will re-main within ranges for at least 12 hours following application. Surface temperature must be a minimum 5°F (3°C) above dew point. Relative humidity should be between 50% and 90%
- 5) **RECOAT OR TOPCOATING:** Multiple coats of this product are acceptable. If you opt to recoat this product, you must first be sure that all of the volatile components have evaporated from the coating during the curing process. Test the coating before recoating or top coating: press the coating with your thumb to test if the fingerprint impression is left on the surface. If no impression is left, then the recoating or top coating can be started. Inspect the coating to ensure no epoxy blushes were developed before recoating or top coating. Any blush must be removed before to recoating or top coating; use regular detergent cleaner to remove any blush. Colder temperatures require more cure time for the product before recoating or top coating. When recoating this product with subsequent coats of the urethane, it is advisable to apply the recoat before 24 hours passes. Also, it is advisable to de-gloss the previous coat to insure a trouble-free bond.
- 6) **CLEANUP:** Use water-soluble solvent or soap with water after the coating dries.
- 7) **FLOOR CLEANING:** Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.
- 8) **RESTRICTIONS:** Before the coating is fully cured restrict the use of the floor to light traffic and mild chemicals. Let the floor remain dry for the full cure cycle. Surface may be slippery when wet, keep surface dry and clean. Some cleaners may affect the color of the floor; test each cleaner in a small area to check if the color of the floor is affected

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND OUR LIABILITY LIMITATIONS

*We warrant that the information supplied by GlobMarble is accurate to the best of our knowledge and our products manufactured to strict quality assurance specifications, information supplied about our products is not a representation or a warranty. GlobMarble product supplied on the condition that you shall make your own tests to determine our product suitability for your particular purpose. Listed physical properties are typical and should not be construed as specifications. Any product use or application other than recommended herein is the sole responsibility of the user GlobMarble products shall not be liable for coat or labor or direct and/or indirect consequential damage. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABILITY OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** Our liability is limited to the net selling price of our product or the replacement of our product, at manufacturer/seller's option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. READ THE MATERIAL SAFETY DATA SHEET BEFORE USING, AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.*

GLOBMARBLE INC.