




# SCHÖNOX AP

## Synthetic Gypsum Based Self-leveling Compound

Especially suitable on all gypsum and cement based substrates as well as on mastic asphalts. Designed for refurbishment work in interior areas. SCHÖNOX AP can be installed up to 2".



### Product characteristics

- EMICODE EC 1<sup>PLUS</sup>: very low emission
- Benefits to Environment and Health
- does not support mold growth
- for interior use only
- self-leveling
- high hardness and strength
- suitable for underfloor heating systems
- layer-thickness above 1/16" up to 2"
- pumpable
- very low shrinkage
- free of cracks even in higher thicknesses
- suitable for castor wheel loadings
- dust reduced
- very smooth surface
- exceeds minimum Ff/FI requirements of ASTM and ACI when installed in accordance with the guidelines
- tested in accordance with ASTM C1708

### Applications

**SCHÖNOX AP is suitable for filling, smoothing and leveling of substrates:**

- under flexible coverings
- under wood floor, layer thickness at least 1/8" (use elastic adhesives only)

### Substrates

**SCHÖNOX AP is suitable on:**

- gypsum substrates
- concrete, cement substrates
- old substrates such as ceramic tiles, terrazzo and sheet vinyl
- old, water-resistant adhesive residues
- OSB board, plywood (well screwed down and/or bonded) prior to install flexible coverings.

### Requirements of substrate

- Subfloors must be smooth, sound, clean, dry and free of any contaminants which may hinder adhesion.
- Surface treatments or any "friable" areas of the subfloor must be mechanically removed back to a sound base and the substrate repaired with SCHÖNOX repair compounds as required.
- Thoroughly vacuum all dust or other loose material.
- All slabs on or below grade level must be known to have an intact vapor retarder directly beneath the concrete in conformance to the relevant standards. If in doubt, please contact our SCHÖNOX representative for further advice.
- This product is not a vapor barrier and will allow free passage of moisture. Follow the directions of the floor covering manufacturer regarding the maximum allowable substrate moisture content

and test the substrate prior to installing SCHÖNOX AP. Where substrate moisture exceeds the maximum allowed then application of SCHÖNOX SDG PLUS, SCHÖNOX MR 18 or SCHÖNOX EPA may be used to suppress residual moisture.

- Gypsum substrates should always be dry. Do not use moisture mitigation systems on gypsum substrates.
- Old water-soluble adhesives should be removed completely, old water-resistant adhesives should be mechanically removed as far as possible. The complete mechanical removal of cutback (i.e. grinding, sanding, blasting) can be hazardous as old cutback adhesive may contain asbestos. Do not sand or grind adhesive residue. Refer to the Resilient Floor Covering Institute's publication "recommended work practice for removal of resilient floor coverings" for instruction. Prime remaining adhesive residues accordingly.
- Old floors such as ceramic tiles should be thoroughly cleaned and abraded.
- Prior to install ceramic tiles we recommend to use SCHÖNOX US.
- The requirements of the relevant valid standards (such as ASTM 2873-13), guidelines and data sheets apply.

### Priming

- **porous substrates such as**
  - concrete, cement substrates prime with SCHÖNOX VD (1:3) or KH FIX.
- **non porous, smooth, sound substrates such as**
  - ceramic tiles
  - old water-resistant adhesive residues, removed as far as possible
  - OSB board, plywood (well screwed down and/or bonded) prime with SCHÖNOX SHP.
- **gypsum substrates (sanded and vacuumed)** prime with SCHÖNOX KH FIX.

### Mixing ratio

- mix each 25 kg / 55 lb. bag with 6.0 liters / 6.3 quarts of water
- we recommend to extend SCHÖNOX AP with dry, clean aggregate (aggregate is added last) at a layer thickness above 1": Type and amount of aggregate used will affect product performance. As qualities of locally available aggregates vary, we recommend to perform tests prior to use on a larger scale.

Do not overwater! Foam while mixing, or settling of the sand aggregate while placing, indicates overwatering.

### Technical data

- pot life: approx. 30 minutes
- ready for foot traffic: approx. 2 hours
- ready for covering:
  - after approx. 16 hours at 1/8"
- working temperature: 41°F - 90°F
- coverage per unit:
  - approx. 60 - 70 sq.ft. at 1/8" (depending on substrate conditions and aggregate used)
- compressive strength (ASTM C109):
  - 5800 psi / 35 N/mm<sup>2</sup> / 400 kg/cm<sup>2</sup> after 28 days
  - 2100 psi / 13 N/mm<sup>2</sup> / 140kg/cm<sup>2</sup> after 1 day
- flexural strength (ASTM C348):
  - approx. 1400 psi / 8 N/mm<sup>2</sup> after 28 days
- tensile strength (ASTM C1583) at 1/8":
  - above 400 / 2.5 N/mm<sup>2</sup> psi after 3 days
- initial Set (ASTM C191):
  - approx. 110 minutes
- final Set (ASTM C191):
  - approx. 120 minutes
- cured density: 110 lbs. / cu.ft.
- UL-classified in accordance with ASTM E84 (ANSI/UL 723):
  - Flame Spread 0; Smoke Development 0

All values are approximate, are subject to local climatic fluctuations based upon conditions at 70°F with atmosphere of less than 65 % relative humidity following the recommended mixing ratio. Do not install underlayment or topping before the substrate has dried thoroughly.



# SCHÖNOX AP

## Recommended method of working

### ■ Adequate ventilation is essential when SCHÖNOX AP is being worked to ensure faster drying.

- Using a clean mixing drum, add SCHÖNOX AP to cold, clean water to form a homogeneous mixture. Mix thoroughly for approx. 3 minutes using a heavy-duty drill (min. 600 rpm) to obtain a lump-free mix. Then pour the mix and spread using a smoothing trowel. Even surfaces are easily achieved using a pin leveler. In higher thicknesses using a spike roller is recommended.
- Contact to vertical structures should be avoided by using SCHÖNOX FOAMTAPE. Avoid direct contact to metallic constructions (e.g. heating pipes), which can lead to corrosion.
- If a second layer of leveling compound is to be applied, prime the first layer with SCHÖNOX KH FIX after drying. The maximum layer thickness must not be exceeded in case of two layer applications. The second layer must not exceed the layer thickness of the first layer.
- Protect curing SCHÖNOX AP layers from high ambient temperatures, direct sunlight and draughts.
- Clean tools in water immediately.

## Packaging

- 25kg / 55lb. net weight in paper bags

## Storage

- Store in cool and dry conditions.
- Shelf life: 12 months unopened.
- End of shelf life does not generally indicate the end of the products suitability for the intended use. Always test in a small area.

## Disposal

- Empty packaging and dispose of in accordance with federal, state and local waste disposal regulations.

## VOC Content

- 0g/l (calculated), SCAQMD 1113

## LEED

May help contribute to LEED v4 certification of projects in the categories:

- EQc2 - 3 points  
Low-Emitting Materials
- MRc1 - up to 2 points

Life-Cycle Impact Reduction

- MRc2 - 1 point  
Environmental Product Declaration
- MRc3 - 1 point  
Sourcing of Raw Materials
- MRc4 - 1 point  
Material Ingredients

## Environmental Product Declaration (EPD)

- Declaration number:  
EPD-DIV-2013311-EN

## Instructions

- Do not use in areas of constant water exposure (such as interior swimming pools).
- Always install an adequate number of properly located test areas, to include the finish flooring, to determine the suitability of the product for its intended use. As floor coverings vary, always contact and rely upon the floor covering manufacturer for specific directions such as maximum allowable moisture content, adhesive selection, and intended end use of the product.
- Low substrate temperatures and/or high ambient humidity require longer drying times.

## Precautions

- SCHÖNOX AP contains gypsum and sand aggregate. Avoid eye and skin contact. In case of contact, rinse immediately with plenty of water. In case of contact with eyes seek additional medical advice. Mix in a well ventilated area and avoid breathing powder or dust.
- Never mix with cement or additives other than SCHÖNOX approved products. Observe the basic rules of concrete work. Do not install below 41°F surface temperature. Install quickly if substrate is warm.

Prior to each use of any SCHÖNOX product, the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [www.schonox.us](http://www.schonox.us), or by calling the HPS SCHÖNOX Technical Service Department at 855-391-2649. Nothing contained in any SCHÖNOX materials relieves the user of the obligation to read and follow the warnings and instruction for each SCHÖNOX product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to product use. This product data sheet supersedes all previous editions.



Management system certified to ISO 9001 and 14001 by SQS.

### In North America provided by:

HPS North America, Inc  
511 Wilhite Street Florence, AL 35630  
Phone: 256.246.0345  
Fax: 256.246.0346  
Email: [info@hpsubfloors.com](mailto:info@hpsubfloors.com)  
<http://www.hpsubfloors.com>

**SCHÖNOX**®

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY • FOR PROFESSIONAL USE ONLY  
SCHÖNOX products are supplied in the USA by SCHÖNOX HPS North America, a business unit of HPS North America, Inc. (HPS SCHÖNOX).

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call GBK/Infotrac ID 108313 at 1 800 535 5053 (USA) or 001 352 323 3500 (International). HPS SCHÖNOX warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. HPS SCHÖNOX SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. HPS SCHÖNOX SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SCHÖNOX products are subject to the Terms and Conditions of Sale which are available at [www.schonox.us](http://www.schonox.us).