




SCHÖNOX SL

Cement Based Rapid Drying, Smoothing and Finishing Compound

Suitable to provide a smooth finish on various substrates in interior areas. SCHÖNOX SL can be installed as a true featheredge.



Product characteristics

- EMICODE EC 1^{PLUS} R: very low emission
- for interior use only
- featheredge achievable
- exceptional hardness and strength
- fast drying
- suitable for underfloor heating systems
- layer thickness above featheredge up to 1/4", in small, well-defined areas up to 1" (on wooden floors up to 1/8")
- suitable for castor wheels loadings
- very smooth surface
- moisture resistant (interior only), no moisture vapor emission limitations on properly prepared concrete
- conforms with uSD 96/98/BC

Applications

SCHÖNOX SL is suitable for patching, smoothing and leveling of:

- concrete, cement substrates
- floor leveling compounds
- gypsum substrates
- old substrates such as ceramic tiles
- old, water-resistant adhesive residues
- wooden substrates

as well as for filling, smoothing and leveling of unheated, cement based substrates under:

- SCHÖNOX Moisture Mitigation Systems

Requirements of substrate

- Subfloors must be smooth, sound, clean, dry and free of any contaminants which may hinder adhesion.
- Surface treatments or any "friable" areas of the subfloor must be mechanically removed back to a sound base and the substrate repaired with SCHÖNOX repair compounds as required.
- This product is not a vapor barrier and will allow free passage of moisture. Follow the directions of the floor covering manufacturer regarding the maximum allowable substrate moisture content and test the substrate prior to installing SCHÖNOX SL. Where substrate moisture exceeds the maximum allowed then application of SCHÖNOX SDG PLUS, SCHÖNOX MR 18 or SCHÖNOX EPA may be used to suppress residual moisture.
- Do not use SCHÖNOX SL where hydrostatic pressure conditions exist or where moisture vapor emissions exceed the recommended levels.
- Gypsum substrates should always be dry. Do not use moisture mitigation systems on gypsum substrates.

- Old water-soluble adhesives should be removed completely, old water-resistant adhesives should be mechanically removed as far as possible. The complete mechanical removal of cutback (i.e. grinding, sanding, blasting) can be hazardous as old cutback adhesive may contain asbestos. Do not sand or grind adhesive residue. Refer to the Resilient Floor Covering Institute's publication "recommended work practice for removal of resilient floor coverings" for instruction. Prime remaining adhesive residues accordingly.

- The use of trowelable patching compounds to mask the presence of adhesive residues can be used successfully, but only when the new adhesive to be used does not react with the old residue, and the floor covering to be installed will not be affected by adhesive bleed-through.

- All cement based or wooden substrates must be solid, thoroughly clean and free of oil, wax, grease, asphalt, latex and gypsum compounds, curing compounds, sealers and any contaminant that might act as a bond breaker. If necessary, mechanically clean the floor down to sound, solid surface.

- Solidly bonded non-porous substrates such as ceramic tile and terrazzo must be thoroughly cleaned and abraded including the complete removal of existing waxes and sealers, dust, dirt, debris and any other contaminant that may act as a bond breaker.

- Substrates such as epoxy or urethane based sealers/coatings are primed with SCHÖNOX SHP following the referring product data sheet prior to apply SCHÖNOX SL.

- Porous substrates as required for installing resilient flooring using wet set adhesives are achieved applying underlayments or patching compounds above 1/8".

- The requirements of the relevant valid standards (such as ASTM F710-11), guidelines and data sheets apply.

- Vacuum substrates thoroughly.

Priming

- **porous substrates such as:**

- concrete, cement substrates
- OSB board, plywood (well screwed and/or bonded)
- no priming required.

- **non porous substrates such as:**

- ceramic tiles (thoroughly cleaned and abraded)
- terrazzo
- water-resistant adhesive residues (removed as far as possible)
- no priming required.

Technical data

- pot life: approx 10 - 20 minutes
- ready for foot traffic: after approx. 20 minutes
- ready for covering:
 - after approx. 20 minutes when applied as a true featheredge
- working temperature: 41°F - 90°F
- coverage per unit:
 - approx. 200 sq.ft. when applied as a true featheredge
 - approx. 35 sq.ft. at 1/8" (depending on substrate conditions)
- compressive strength (ASTM C109):
 - 25 N/mm² / 3700 psi after 28 days
- flexural strength (ASTM C348):
 - approx. 7 N/mm² / 1300 psi after 28 days
- classified in accordance with ASTM E84 (ANSI/UL 723):
 - Flame Spread 0; Smoke Development 0

All values are approximate, are subject to local climatic fluctuations based upon conditions at 70°F with atmosphere of less than 65 % relative humidity following the recommended mixing ratio. Do not install underlayment or topping before the substrate has dried thoroughly.



SCHÖNOX SL

- **gypsum substrates (sanded and vacuumed)** prime with SCHÖNOX KH FIX.

Mixing ratio

- mix each 4.5kg / 10lb. bag with 1.9 liters / 2.0 quarts of water

Recommended method of working

- Using a clean mixing bucket, add SCHÖNOX SL to cold, clean water to form a homogeneous mixture. Mix thoroughly for approx. 3 minutes using a heavy-duty drill (min. 600 rpm) to obtain a lump-free mix. Or mix smaller volumes by hand approx. 2 - 3 minutes to consistency. Apply, smooth and shape using a stainless steel smoother or a smoothing trowel.
- Do not mix more material than can be applied within 15 minutes.
- Protect curing SCHÖNOX SL layers from high ambient temperatures, direct sunlight and draughts.
- Clean tools in water immediately.

Packaging

- 4.5kg / 10lb. net weight in paper bags

Storage

- Store in cool and dry conditions.
- Shelf life: 12 months unopened.
- End of shelf life does not generally indicate the end of the products suitability for the intended use. Always test in a small area.

Disposal

- Empty packaging and dispose of in accordance with federal, state and local waste disposal regulations.

VOC Content

- 0g/l (calculated), SCAQMD 1113

LEED

May help contribute to LEED v4 certification of projects in the categories:

- EQc2 - 3 points
Low-Emitting Materials
- MRc1 - up to 2 points
Life-Cycle Impact Reduction
- MRc2 - 1 point
Environmental Product Declaration
- MRc4 - 1 point
Material Ingredients

Environmental Product Declaration (EPD)

- Declaration number: EPD-DIV-2013311-EN

Instructions

- Do not use in areas of constant water exposure (such as interior swimming pools).
- Always install an adequate number of properly located test areas, to include the finish flooring, to determine the suitability of the product for its intended use. As floor coverings vary, always contact and rely upon the floor covering manufacturer for specific directions such as maximum allowable moisture content, adhesive selection, and intended end use of the product.
- Low substrate temperatures and/or high ambient humidity require longer drying times.

Precautions

- SCHÖNOX SL contains Portland cement. Avoid eye and skin contact. In case of contact, rinse immediately with plenty of water. In case of contact with eyes seek additional medical advice. Mix in a well ventilated area and avoid breathing powder or dust.
- Never mix with cement or additives other than SCHÖNOX approved products. Observe the basic rules of concrete work. Do not install below 41°F surface temperature. Install quickly if substrate is warm.

Prior to each use of any SCHÖNOX product, the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at www.schonox.us, or by calling the Technical Service Department at 855-391-2649. Nothing contained in any SCHÖNOX materials relieves the user of the obligation to read and follow the warnings and instruction for each Schönox product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to product use. This product data sheet supersedes all previous editions.



Management system certified to ISO 9001 and 14001 by SQS.

In North America provided by:

HPS North America, Inc
511 Wilhite Street Florence, AL 35630
Phone: 256.246.0345
Fax: 256.246.0346
Email: info@hpsubfloors.com
<http://www.hpsubfloors.com>

SCHÖNOX[®]

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY • FOR PROFESSIONAL USE ONLY
SCHÖNOX products are supplied in the USA by SCHÖNOX HPS North America, a business unit of HPS North America, Inc. (HPS SCHÖNOX).

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call GBK/Infotrac ID 108313 at 1 800 535 5053 (USA) or 001 352 323 3500 (International). HPS SCHÖNOX warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. HPS SCHÖNOX SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. HPS SCHÖNOX SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SCHÖNOX products are subject to the Terms and Conditions of Sale which are available at www.schonox.us.