

SYSTEM DATA SHEET

Sikafloor® DecoDur Quartz TG

DECORATIVE EPOXY AND COLORED QUARTZ MORTAR ENGINEERED WITH SIKAFLOOR® - 217 @ 3/16" - 1/4" (4.7 - 6.3 MM)

PRODUCT DESCRIPTION

Sikafloor® DecoDur Quartz TG is a troweled floor system built with a high solids epoxy and colored quartz aggregates. The system produces a robust, decorative, low maintenance, seamless flooring with excellent durability and chemical resistance. Sikafloor® DecoDur Quartz TG is typically installed @ 3/16" - 1/4" (4.7 - 6.3 mm).

USES

Sikafloor® DecoDur Quartz TG may only be used by experienced professionals.

- Break rooms and cafeterias
- Pharmaceutical plants
- Laboratories
- Hospitals & health care facilities
- Educational facilities
- Locker rooms areas
- Prisons/correctional facilities
- Stadiums

CHARACTERISTICS / ADVANTAGES

- Lower maintenance and life cycle cost vs. other flooring options
- Tough, durable and seamless floor
- Customizable to compliment any decor
- Very low VOC
- A wide range of textures and finishes available
- Optional Integral cove base and curbs available
- Crack-bridging and waterproofing membrane options

SYSTEM INFORMATION

System Structure

Sikafloor® DecoDur Quartz TG ~ 3/16" - 1/4" (4.7 - 6.3 mm)



Description	Products	Thickness mils
1. Primer	Sikafloor®-161 Sikafloor®-217	8 - 10
2. Mortar	+ Trowel Grade Quartz + Sikafloor® Decorative Quartz	3/16"- 1/4"
3. Grout Coat	Sikafloor®-217 Thixo Lite*	12 -16
4. Top Coat	Sikafloor®-217 Thixo lite	5 - 12
Options		
Primers	Sikafloor®-1610 Sikafloor®-165 FS	8 - 10 8 - 10
2 nd Grout Coat	Sikafloor®-217 Thixo Lite* Sikafloor®-511**	5 - 12 12 - 16
Top Coats	Sikafloor®-340*** Sikafloor®-315 N *** Sikafloor®-304 W****	4 - 6 4 - 6 5 - 8

* Sikafloor®-217 Thixo Lite, second grout coat may be required

** Sikafloor-217 Thixo Lite may be replaced by Sikafloor-511 for greater UV resistance, fast cure time

*** Sikafloor-340 and Sikafloor-315 N clear would be an optional top coat increased chemical resistance

**** Sikafloor-304 W would be an optional top coat on top of Sikafloor-217 N for gloss reduction or matte finish

Nominal thickness 3/16" - 1/4" (4.7 - 6.3 mm)

Minimum thickness 3/16" (4.7 mm).

Volatile organic compound (VOC) content Please refer to the individual Product Data Sheets

Water Absorption	0.13 % 2 hours boiling	ASTM C413 at 73°F (23°C) and 50% R.H
Shore D Hardness	80	ASTM D2240 at 73°F (23°C) and 50% R.H
Abrasion Resistance	58 mg loss (CS-17/1000 rotations/1000g)	ASTM D4060 at 73°F (23°C) and 50% R.H
Indentation	1.30%	(MIL-PRF-24613)
Compressive Strength	7,250 psi (51.2 MPa)	ASTM C579 at 73°F (23°C) and 50% R.H
Tensile Strength	5,078 psi (34 MPa)	ASTM D638 at 73°F (23°C) and 50% R.H
Flexural Strength	9,284 psi (64 MPa)	ASTM D790 at 73°F (23°C) and 50% R.H
Tensile Adhesion Strength	>400 psi (2.7 MPa) (100 % concrete failure)	ASTM D4541 at 73°F (23°C) and 50% R.H
Chemical Resistance	Contact Sika Technical Service for specific information.	
Coefficient of Friction	0.6	ANSI 326.3 at 73°F (23°C) and 50% R.H

APPLICATION INFORMATION

Coverage

Description	Products	Approximates Sq.Ft./kit
1.Primer	Sikafloor®-161 Sikafloor®-217 +	900@8mils 540@3/16" 4.8 bags per
2.Mortar	Trowel Grade Quartz +	4.5 gallon kit 1.2 bags per
3.Grout Coat	Sikafloor® Decorative Quartz	4.5 gallon kit
4.Top Coat	Sikafloor®-217 Thixo	600@12mils
	Sikafloor®-217 Thixo	1,440@5mils
Options		
Primers	Sikafloor®-1610	900@8mils
	Sikafloor®-165 FS	1,000@8mils
2 nd Grout Coat	Sikafloor®-217 Thixo Lite	1,440@5mils
	Sikafloor®-511	1,110@12mils
	Sikafloor®-340	6,000@4mils
Top Coats	Sikafloor®-315 N	2,400@4mils
	Sikafloor®-304 W NA	595@5mils

Ambient Air Temperature Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature Minimum/Maximum 50/85 °F (10/30 °C)

PRODUCT INFORMATION

Packaging Please refer to the individual Product Data Sheets

Shelf Life Please refer to the individual Product Data Sheets

Storage Conditions Please refer to the individual Product Data Sheets

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Primer

Priming for concrete substrate is required. Prime with either Sikafloor®-160, Sikafloor®-161, Sikafloor®-1610 or Sikafloor®-165 FS.

Allow the primer to cure, varies with temperature and humidity. Please refer to the individual most current and respective Product Data Sheet for specific and detailed information.

Mortar

Premix each component separately. Measure out 32 ounces (1 quart) of Sikafloor®-217 Part A and 16 ounces (1 pint) of Sikafloor®-217 Part B. Pour A and B into a clean 5 gallon metal bucket. Mix with a very low speed jiffy mixer, mix for 2 to 3 minutes and until uniform. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in mortar.

During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel to ensure complete mixing. Add 20 Lbs of trowel grade quartz aggregate and 5 lbs Sikafloor® Decorative Quartz mix for an additional minute and until uniform. Mix only that quantity that can be used within its pot life and until uniform.

Place mixed mortar using a screed box, gauge rake, or steel trowel. Place as evenly as possible. Using a power trowel (with plastic blades) or a steel trowel by hand compact the mortar. Do not over trowel and do not

finish the last 3 - 4 inches of the placed mortar path, as this will make the transition of the next pass of mortar more difficult to finish. Use floor lights to examine finished work closely to assure complete closing and to identify any trowel marks or imperfections. No holes or tear marks should be visible. After cure scrape with the edge of a steel trowel any high rough spots and sweep and vacuum the surface.

Grout Coat

Sikafloor®-217 Thixo Lite: Mixing Ratio - 2 : 1 by volume. Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes and until uniform using a low speed drill (300-450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing.

Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Apply with a flat rubber squeegee or flat metal trowel tightly over a smooth surface. Back rolling may cause bubbling and leave roller marks. Product has a limited Pot Life, see Typical Data. Do not apply by dipping roller into mixing container.

Top Coat

Sikafloor®-217 Thixo Lite is applied with a flat or notched rubber squeegee over a smooth surface. Back rolling is typically done with an 18 in. (455 mm) wide short nap, 3/16 or 1/4 in. (4 to 6 mm), solvent-resistant roller cover. Back roll the Sikafloor®-217 Thixo Lite only to level the squeegee applied material. Over-rolling and late back rolling may cause bubbling and leave roller marks.

Note: The orange peel texture will vary depending on the mill thickness and type of roller used. Do not apply the material above the recommended thickness, cloudiness/whitening may occur.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

AVAILABILITY/WARRANTY

Sikafloor System Sheets describe a series of Sikafloor products installed in progression. For specific information on the individual products mentioned, including, Mixing, Application, Chemical Warnings, First Aid, Handling & Storage, and Clean Up. Please refer to the individual Product Data Sheet, available at www.sikafloorusa.com System sheets are updated periodically.

To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com. Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control. Before applying for protection against specific chemical environments, consult Chemical Resistance Guide or Sika Technical Service.

LIMITATIONS

- Minimum/Maximum substrate temperature: 50°F/85°F (10°C/30°C)
- Maximum relative humidity: 60°F/85°F (15.5°C/30°C)
- Substrate temperature must be 5°F (3°C) above dew point
- Freshly applied Sikafloor materials should be protected from dampness, condensation and water for at least 24 hours
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. UV resistant, light stable topcoats are available where ultimate color/clarity retention is required
- This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the coating
- Do not thin this product. Addition of thinners will slow down the cure and reduce the ultimate properties of this product.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



System Data Sheet
Sikafloor® DecoDur Quartz TG
November 2020, Version 01.01
02081190000000171

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

SikafloorDecoDurQuartzTG-en-US-(11-2020)-1-1.pdf

